

STÄRKETABELLE



UWG (g)	Stärke %	TS %
283	9,65	15,90
288	9,90	16,20
293	10,15	16,40
298	10,40	16,70
303	10,65	16,90
308	10,90	17,20
313	11,10	17,40
318	11,35	17,70
323	11,60	17,90
328	11,85	18,10
333	12,10	18,40
338	12,35	18,60
343	12,60	18,90
348	12,85	19,10
354	13,15	19,40
359	13,40	19,60
364	13,65	19,90

UWG (g)	Stärke %	TS %
369	13,90	20,10
374	14,15	20,40
379	14,40	20,60
384	14,65	20,90
389	14,90	21,10
394	15,20	21,40
399	15,45	21,60
404	15,70	21,90
409	15,95	22,10
414	16,20	22,40
419	16,45	22,60
424	16,70	22,90
429	16,95	23,10
434	17,25	23,40
439	17,45	23,60
444	17,70	23,90
449	17,95	24,10

UWG (g)	Stärke %	TS %
455	18,25	24,40
460	18,55	24,60
465	18,75	24,90
470	19,05	25,10
475	19,30	25,40
480	19,55	25,60
485	19,90	25,90
490	20,15	26,10
495	20,40	26,30
500	20,65	26,60
505	20,90	26,80
510	21,10	27,20
515	21,40	27,50
520	21,70	27,80
525	21,90	28,00
530	22,20	28,20
535	22,50	28,50